





CLOSED CELL FOAM TUBULAR GRIP MATERIAL



122 BLACK



125 OFF WHITE



222 YELLOW



321 ORANGE



429 SPRING GREEN



522 RED



721 BLUE



722 DARK BLUE



723 BRIGHT BLUE




822 LIGHT GRAY



823 MEDIUM GRAY



824 DARK GRAY



927 BROWN

Note: Due to printing limitations, colors pictured cannot be guaranteed to match actual material.



Engineered For Success.

Grip Material Physical Properties

TYPE	700	900	1200	1600	2400
Density (pcf) – ASTM D1056	6 - 9	8 - 12	11 - 15	13 - 17	18 - 24
Shore Hardness – ASTM D2240	35 - 55 (00)	45 - 65 (00)	45 - 65 (00)	15 - 35(A)	30 - 50 (A)
Compression Deflection (25%) psi – ASTM D1056	3 - 7	3.5 - 7.5	5 - 9	9 - 13	13 - 21
Water Absorption (By Wt. % Max.) – ASTM D1056	10	5	5	5	5
Tensile Strength (psi) – ASTM D412 (Die A)	50 min.	75 min.	100 min.	175 min.	200 min.
Elongation – ASTM D412 (Die A)	100 min.	125 min.	125 min.	125 min.	175 min.
Temperature Range ASTM D1056	-20° - 200°F	-20° - 200°F	-20° - 200°F	-40 - 200°F	-40 - 200°F
ASTM D1056-14 Specification	2B1 / 2B2	2B1 / 2B2	2B2	2B3	2B4 / 2B5

ARMACELL LLC

1004 Keisler Road Conover, NC 28613
 TEL: 919 304-3846 ext. 3133 or 828 464 5880
 FAX: 828 465-3199
 info.us@armacell.com
 www.armacell.us

7600 Oakwood Street Extension • Mebane, NC 27302



Engineered For Success.

Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, as of date of printing, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information are provided as a technical service and are subject to change without notice.

© 2014 Armacell LLC

Printed in United States of America