

ENGINEERED FOR VERSATILITY

EnsoLine[®] EPDM 2A3


Closed cell EPDM rubber tube / rod / profile

// ASTM D 1056 2A3

// Higher density closed cell expanded rubber

// Color black

www.armacell.us



 **armacell**[®]
ArmaComp[™]

ENSOLINE® EPDM 2A3 | Closed cell EPDM rubber tube / rod / profile

EnsoLine EPDM 2A3: Armacell (Conover, NC Plant) manufactures a black, closed cell, 16 - 22 lb/ft³ (256 - 352 kg/m³) density, EPDM rubber tube / rod / profile product EPDM 2A3, that meets the requirements of ASTM D 1056 2A3. EPDM 2A3 meets the horizontal burn / flame requirements of FMVSS 302 at 0.500" (1/2") (12.7 mm) & higher.

TECHNICAL DATA SHEET | TUBE / ROD / PROFILE (effective 12/28/2021)

POLYMER: EPDM

Physical Property	Test Method	Unit	Value	
ASTM D 1056 Designation	-	-	2A3	
Cell Structure	-	-	Closed	
Color	-	-	Black	
Compression Deflection 25%	ASTM D 1056	psi kPa	9 - 13 62.1 - 89.6	
Compression Deflection 25%, after Heat Aging	ASTM D 1056	%	± 30	
Compression Set (Room temp)	ASTM D 1056	%	25 max	
Density	ASTM D 1056	lb/ft ³ kg/m ³	16 - 22 256.3 - 352.4	
Elongation	ASTM D 412 (Die A)	%	150 min	
Flammability	FMVSS 302	in mm	0.500 and higher 12.7 and higher	
Hardness, Durometer Shore 00	ASTM D 2240	-	35 - 55	
Service Temperature	Low	ASTM D 1056	°F °C	-65 -53.8
	High Intermittent	-	°F °C	200 93.3
Tensile Strength	ASTM D 412 (Die A)	psi kPa	120 min 828 min	
Water Absorption	ASTM D 1056	%	5 max	

All data and technical information are based on results achieved under the specific conditions defined according to the testing standards referenced. Despite taking every precaution to ensure that said data and technical information are up to date, Armacell does not make any representation or warranty, express or implied, as to the accuracy, content or completeness of said data and technical information. Armacell also does not assume any liability towards any person resulting from the use of said data or technical information. Armacell reserves the right to revoke, modify or amend this document at any moment. It is the customer's responsibility to verify if the product is suitable for the intended application. The responsibility for professional and correct installation and compliance with relevant building regulations lies with the customer. This document does not constitute nor is part of a legal offer to sell or to contract.

At Armacell, your trust means everything to us, so we want to let you know your rights and make it easier for you to understand what information we collect and why we collect it. If you would like to find out about our processing of your data, please visit our [Data Protection Policy](#).

© Armacell, 2022. All rights reserved. Trademarks followed by © or TM are trademarks of the Armacell Group.
EnsoLine EPDM 2A3 | DataSheet | 112022 | NA | EN-A

ABOUT ARMACELL

As the inventors of flexible foam for equipment insulation and a leading provider of engineered foams, Armacell develops innovative and safe thermal, acoustic and mechanical solutions that create sustainable value for its customers. Armacell's products significantly contribute to global energy efficiency making a difference around the world every day. With 3,100 employees and 26 production plants in 18 countries, the company operates two main businesses, Advanced Insulation and Engineered Foams. Armacell focuses on insulation materials for technical equipment, high-performance foams for high-tech and lightweight applications and next generation aerogel blanket technology.

For more information, please visit:

www.armacell.us

info.cf.us@armacell.com

800-973-0490

