



SUBMITTAL SHEET (effective 10/06)

Polymer Base: Jancork			F-00746 (Cork)
Physical Properties	Unit	Test Method	Typical Results
Density	g/cm ³	ASTM D 3575	0.6
	lb/ft ³	ASTM D 3575	(37.5)
Hardness, Durometer Shore "A"		ASTM D 2240	60
Tensile Strength	kPa	ASTM D 412 (Die A)	1380
	psi	ASTM D 412 (Die A)	200
C-Tear Strength	kN/m	ASTM D 412 (Die C)	6.8
	%lb/in.	ASTM D 412 (Die C)	(39)
Elongation	%	ASTM D 412 (Die A)	100%
Resilience	%	ASTM D 2632	35%
Shrinkage			
40' at 70°C (158°F)		RMA (FIA)	< 2%

ASTM D 1056 designation: SAE J 18 APR2002 designation: ASTM D 6576:

For updates to this document please refer to our website.

Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information are subject to change without notice.

Armacell LLC • 7600 Oakwood Street Ext. • Mebane NC 27302 email: info.us@armacell.com • www.armacell.com

Mebane, NC • 919-304-3846 ext 3934 • fax: 919-304-8958 Spencer, WV • 800-638-6312 • fax: 304-927-5731

© 2006 Armacell LLC F-00746 01 10 06 NA NA ALL ARMACELL FACILITIES IN NORTH AMERICA ARE ISO 9001:2000 OR ISO/TS 16949:2002 CERTIFIED